

ROSE TALBERT

P A I N T S

7950 CHEM-ENAMEL GLOSS BLACK

7950 Chem-Enamel is a general purpose alkyd gloss enamel. Chem-Enamel has good exterior gloss & color retention. It is fast drying, and has good flexibility and film toughness.

1. RECOMMENDED USES: Use for the finishing or refinishing of industrial, construction, and agricultural equipment.

2. LIMITATIONS: Do not paint over chalk, dust, dirt, grease, mildew, rusty or glossy surfaces. For interior/exterior use. Apply only when the atmospheric temperature and surface temperature will remain above 50⁰ F, and not in foggy or rainy weather.

3. RECOMMENDED PRIMERS:

-9072 & 9074-66 HS Phenolic Primers

-8900 DTM Primer

4. COLOR: Black

5. TECHNICAL DATA:

DRYING TIME: @ 77⁰F and 50% RH:
30min.. - TO TOUCH
1-2 hr. - TO HANDLE
**TO RECOAT
-Before 3 hrs.
-After 48 hrs.

FINISH: Gloss

COVERAGE: 648 SQ. FT. @ 1 MIL DFT

VISCOSITY: 55-60 KU

VEHICLE TYPE: Short oil alkyd resin

SOLIDS BY VOLUME: 40.4 \pm 2.0%

WEIGHT PER GALLON: 8.44 LB. \pm 2.0%

FLASH POINT: 45⁰F.

VOC 433 g/l

6. SURFACE PREPARATION: Surface must be dry and free of chalk, dirt, grease, oil and mildew. Hand tool cleaning (SSPC-SP2) or power tool cleaning (SSPC-SP3) is preferred.

7. MIXING: One component. Stir thoroughly in a lifting motion before using.

8. THINNING: Xylene if necessary.

9. SHELF LIFE: 12 Months

10. CLEAN-UP: Xylene.

11. CAUTION: PROTECT FROM FREEZING: VAPOR MAYBE HARMFUL. BREATHING OF VAPOR MAY CAUSE RESPIRATORY IRRITATION. USE ONLY WITH ADEQUATE VENTILATION. CAUSES EYE IRRITATION. DO NOT TAKE INTERNALLY. IN CASE OF SPILLAGE, ABSORB AND DISPOSE OF ACCORDING TO LOCAL REGULATIONS. KEEP OUT OF REACH OF CHILDREN.

FIRST AID: IN CASE OF SKIN CONTACT, FLUSH WITH PLENTY OF WATER; FOR EYES, FLUSH WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION. IF EFFECTED BY INHALATION, MOVE TO FRESH AIR. **IF SWALLOWED, CALL PHYSICIAN IMMEDIATELY. DO NOT INDUCE VOMITING.**

NOTE: ALL TECHNICAL ADVICE, RECOMMENDATIONS AND SERVICES RENDERED BY THE SELLER IS GRATIS. SELLER ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. ANY INFORMATION CONTAINED HEREIN IS BELIEVED BY THE SELLER TO BE RELIABLE AND INTENDED FOR THE USES BY PERSONS HAVING SKILL AND KNOW-HOW, AT THEIR DISCRETION AND RISK. FINAL DETERMINATION OF THE SUITABILITY FOR THE USE CONTEMPLATED AND THE MANNER OF USE IS THE SOLE RESPONSIBILITY OF THE USER.

ROSE TALBERT PAINT COMPANY
P.O. BOX 2658
CAYCE-WEST COLUMBIA, S.C. 29171
803 796-0324