

ROSE TALBERT

P A I N T S

9600 WEATHER BARRIER ELASTOMERIC

9600 Weather Barrier Elastomeric is a premium quality elastomeric coating formulated to meet both the commercial & residential markets. It is a high build waterproofing coating made with acrylic resins that provide 517% elongation. 9600

Weather Barrier Elastomeric has passed the 90mi./hr. Wind Driven Rain Test (TTC-555B).

1. RECOMMENDED USES: To be used as a finish coat on exterior masonry, stucco, concrete block, poured & pre-cast concrete, brick, steel (primed), aluminum, galvanized metal, wood (primed), and previously coated surfaces.

2. LIMITATIONS: Apply when air, surface, and product temperatures are above 50 deg.F (10 deg.C), and the surface temperature is at least 5 deg.F (3 deg.C) above the dew point. Avoid application late in the day when dew & condensation are likely to form or if rain is threatening. Protect from freezing. Not recommended for use on surfaces demonstrating high vapor or hydrostatic pressure or for immersion service. For exterior use only. Surface must be clean, dry, and free of dirt, loose & peeling paint, mildew, chalk, and other contaminants.

3. APPLICATION: Apply by airless spray, roller or brush.

Apply by brush to small areas only. When applying by roller, the final passes should be completed in a downward direction to ensure a uniform appearance. Maintain a wet edge for sheen uniformity.

Permissible Temperatures during Application:

Material:	50 to 90 deg.F	10 to 32 deg.C
Ambient:	50 to 100 deg.F	10 to 38 deg.C
Substrate:	50 to 100 deg.F	10 to 38 deg.C

4. COLOR: White & Custom Colors.

5. TECHNICAL DATA:

DRYING TIME: @ 77⁰F - 50 % R.H.
3 hr.- TO THE TOUCH
6 - 8 hr. - TO RECOAT

GLOSS: Flat-Smooth

COVERAGE: 55 SQ. FT. @ 16 MIL DFT

VISCOSITY: 100-105 KU

VEHICLE TYPE: Acrylic

SOLIDS BY VOLUME: 55.0 ± 2.0%

WEIGHT PER GALLON: 12.6 LB. ± 2.0%

POINT: N/A ⁰F.

VOC 55 g/l

TENSILE STRENGTH (Dry), psi 268.2

ELONGATION (Dry), % 517.0

WATER PONDING (mg/24 hrs)

Permeance (perms) 161.4

Permeability (perm inches) 17.42

Permeability (perm inches) .575

WATER ABSORPTION, %

24 Hours 12.0

7 Days 12.0

CAUSTIC ABSORPTION, %

24 Hours 8.5

7 Days 20.0

180 degree PEEL ADHESION (lbs./inch)

ad=adhesive co=cohesive

Galvanized steel 17.8 co
Transite 3.2 ad
Plywood 12.5 ad

Low Temperature Flexibility: pass

Cracking: none

6. SURFACE PREPARATION: Surface must be dry and free of chalk, dirt, grease, oil and mildew. Cracks must be filled prior to painting. Treatment of cracks is required to obtain the water-resistant protection of the building, and to help prevent further cracking & deterioration. Methods of treatment depend upon the size of the cracks.

Concrete block, cinder block & vertical masonry:

New concrete should cure for at least 30 days and preferably 90 days prior to priming. Fill block with appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. Such coatings must be completely removed for best results. If the coatings appear to be adhering tightly, a masonry sealer may be applied to seal the surface prior to topcoating. One method to check for adhesion is by applying a piece of masking tape. If it peels off easily and has loose particles adhering to it, remove all the chalk or crumbling material before repainting.

7. MIXING: Stir or shake thoroughly before applications. If spray applied, must be back-rolled. Read all label instructions prior to use.

8. THINNING: No thinning is required.

9. SHELF LIFE: 12 Months

10. CLEAN-UP: Warm soapy water.

11. CAUTION: PROTECT FROM FREEZING: VAPOR MAY BE HARMFUL. BREATHING OF VAPOR MAY CAUSE RESPIRATORY IRRITATION. USE ONLY WITH ADEQUATE VENTILATION. CAUSES EYE IRRITATION. DO NOT TAKE INTERNALLY. IN CASE OF SPILLAGE, ABSORB AND DISPOSE OF ACCORDING TO LOCAL REGULATIONS. KEEP OUT OF REACH OF CHILDREN.

FIRST AID: IN CASE OF SKIN CONTACT, FLUSH WITH PLENTY OF WATER; FOR EYES, FLUSH WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION. IF EFFECTED BY INHALATION, MOVE TO FRESH AIR. **IF SWALLOWED, CALL PHYSICIAN IMMEDIATELY. DO NOT INDUCE VOMITING.**

NOTE: ALL TECHNICAL ADVICE, RECOMMENDATIONS AND SERVICES RENDERED BY THE SELLER IS GRATIS. SELLER ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. ANY INFORMATION CONTAINED HEREIN IS BELIEVED BY THE SELLER TO BE RELIABLE AND INTENDED FOR THE USES BY PERSONS HAVING SKILL AND KNOW-HOW, AT THEIR DISCRETION AND RISK. FINAL DETERMINATION OF THE SUITABILITY FOR THE USE CONTEMPLATED AND THE MANNER OF USE IS THE SOLE RESPONSIBILITY OF THE USER.

ROSE TALBERT PAINT COMPANY
P.O. BOX 2658
CAYCE-WEST COLUMBIA, S.C. 29171
803 796-0324