

ROSE TALBERT

P A I N T S

CLEAN 5400 PREMIUM ACRYLIC LOW LUSTRE ENAMEL ZERO VOC

Premium Acrylic Low Lustre Enamel is a premium quality low luster enamel formulated to have all the characteristics of gloss enamel. This tough, high hiding non-yellowing paint is for use in high traffic areas where a flat finish is not recommended. Clean 5000 products are zero VOC and low odor formulation.

1. RECOMMENDED USES: Use as an interior finish on plaster, drywall, masonry, concrete block, primed steel, and wood in homes, hospitals, schools and factories.

2. LIMITATIONS: Do not paint over chalk, dust, dirt, grease, mildew, rusty or glossy surfaces. For interior use only. Apply only when the atmospheric temperature and surface temperature will remain above 50°F, and not in foggy or rainy weather. Do not wash with hard or abrasive cleaners. Use a mild detergent, warm soapy water and soft cloth to remove dirt.

3. RECOMMENDED PRIMERS:

- A. Drywall: 690 Premium Vinyl Emulsion Primer; 5690 Premium Vinyl Emulsion Primer Zero VOC; 250 Bondaplex Interior/exterior.
- B. Plaster: 180 Premium Enamel Undercoat (Alkyd); 690 Premium Vinyl Emulsion Primer.
- C. Wood: 250 Bondaplex Acrylic Primer; 180 Premium Enamel Undercoat (alkyd); 690 Premium Vinyl Emulsion Primer; 5690 Premium Vinyl Emulsion Primer Zero VOC.
- D. Masonry: 690 Premium Vinyl Emulsion Primer; 5690 Premium Vinyl Emulsion Primer Zero VOC; 250 Bondaplex Interior/Exterior Primer.
- E. Concrete Block: 3550 HD Block Filler/ 650 Block Filler; 5550 Heavy Duty Vinyl Block Filler Zero VOC.
- F. Steel: #76 Zinc Chromate Metal Primer; 78 White Metal Primer; 9072 High solids Phenolic Gray Primer; 9075 High solids Phenolic Red Oxide Primer; 8900 Aqua Chen DTM Primer/Finish.
- G. Aluminum: #76 Metal Primer & 8900 DTM Primer.
- H. Galvanized: No primer necessary.

4. COLOR: White & Custom colors.

5. TECHNICAL DATA:

DRYING TIME: @ 77°F @ 50% RH
30 min. - TO TOUCH
2 - 4 hr. - TO RECOAT

FINISH: Eggshell

COVERAGE: 400 SQ. FT. @ 1.32 MIL DFT

VISCOSITY: 95 KU

VEHICLE TYPE: Vinyl Acrylic

SOLIDS BY VOLUME: 32.27 ± 2.0%
WEIGHT PER GALLON: 10.42 LB. ± 2.0%
FLASH POINT: N/A °F
VOC: 0 g/l

6. SURFACE PREPARATION: Surface must be dry and free of chalk, dirt, grease, oil and mildew.

7. MIXING: One component. Stir thoroughly in a lifting motion before using.

8. THINNING: Water if necessary

9. SHELF LIFE: 12 Months

10. CLEAN-UP: Warm soapy water.

11. CAUTION: PROTECT FROM FREEZING: VAPOR MAYBE HARMFUL. BREATHING OF VAPOR MAY CAUSE RESPIRATORY IRRITATION. USE ONLY WITH ADEQUATE VENTILATION. CAUSES EYE IRRITATION. DO NOT TAKE INTERNALLY. IN CASE OF SPILLAGE, ABSORB AND DISPOSE OF ACCORDING TO LOCAL REGULATIONS. KEEP OUT OF REACH OF CHILDREN.

FIRST AID: IN CASE OF SKIN CONTACT, FLUSH WITH PLENTY OF WATER; FOR EYES, FLUSH WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION. IF EFFECTED BY INHALATION, MOVE TO FRESH AIR. **IF SWALLOWED, CALL PHYSICIAN IMMEDIATELY. DO NOT INDUCE VOMITING.**

NOTE: ALL TECHNICAL ADVICE, RECOMMENDATIONS AND SERVICES RENDERED BY THE SELLER IS GRATIS. SELLER ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. ANY INFORMATION CONTAINED HEREIN IS BELIEVED BY THE SELLER TO BE RELIABLE AND INTENDED FOR THE USES BY PERSONS HAVING SKILL AND KNOW-HOW, AT THEIR DISCRETION AND RISK. FINAL DETERMINATION OF THE SUITABILITY FOR THE USE CONTEMPLATED AND THE MANNER OF USE IS THE SOLE RESPONSIBILITY OF THE USER.

ROSE TALBERT PAINT COMPANY
P.O. BOX 2658
CAYCE-WEST COLUMBIA, S.C. 29171
803 796-0324