

Type	Sheen	Spread Rate	Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Waterborne Alkyd	Satin	Up to 400 - 450 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	2 - 4 Hours	6 - 8 Hours*	7 - 10 Days
<b>PRODUCT NAME:</b> Aqua Alkyd Waterborne Alkyd Satin		Aqua Alkyd is a super-premium Int. / Ext. Waterborne Alkyd Enamel in a Satin finish. The product's superior open time, brush leveling and depth of sheen produce a smooth, hard film with the depth of sheen that is characteristic of a traditional alkyd enamel with-out the mess or smell associated with solvent based coatings.						
<b>WHERE TO USE:</b>		For use on primed or previously painted Int./Ext. doors, cabinets, trim, handrails and shelving. Ideal for use on interior or exterior trim, doors and cabinetry. Aqua Alkyd is a hard finish so it not recommended as a general purpose exterior house paint for application to dynamic substrates like wood, vinyl or aluminum siding.						
<b>Surface Preparation:</b>		The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Wax, grease and oil should be removed using a commercial degreaser (such as Krud Kutter). Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Porous surfaces should be primed with the appropriate primer. Remove sanding dust before application of paint or primer.						
<b>Application:</b>		Stir thoroughly before and during use, do not use a high speed drill as this may cause bubbles. Apply by brush, roll or spray. Use a quality nylon/polyester brush and a 3/16" to 3/8" roller. Flow on working from the unpainted into the painted area while maintaining a wet edge. This product has excellent open-time and superior flow and leveling which means it is important to apply it in thin even coats to prevent sagging.  For best results, use quality applicator tools. Do not sacrifice good results by using inexpensive tools. Apply only when surface and air temperatures are between 50°F and 90°F.						
<b>Clean Up:</b>		Clean equipment in warm soapy water. As with all W/B alkyds it is sometimes necessary to clean brushes with hand cleaner or an alkaline cleaner to get all the residual resin out of the brush.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin Type:</b>	Waterborne Alkyd
<b>Solids:</b>	Volume Solids: 40%
<b>Weight Per Gallon:</b>	10.61 lbs. per gallon
<b>Viscosity:</b>	98 – 102 (Krebs Units)
<b>Specular Gloss:</b>	25 – 30% @ 60°
<b>Recommended Film Thickness:</b>	Wet – 3.5 to 4.0 mils Dry – 1.42 to 1.60 mils
<b>Spread Rate:</b>	400 – 450 sq. ft. per gallon.
<b>Re-Coat:</b>	Dry to touch in 2-4 hours, recoat in 6-8 hours at 77 degrees and 50% Rh. Heavy coats, cool temperatures, high humidity or lack of airflow will retard the dry, recoat and cure times. Aqua Alkyd's full adhesion and hardness develop over time, with good drying conditions doors, shelves and cabinets can return to normal service in 3-5 days.
<b>Lead Statement:</b>	<b>WARNING!</b> If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS A BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start find out how to protect yourself and your family by contacting the National Lead Information Hotline 1-800-424-LEAD or log on to <a href="http://www.epa.gov/lead">www.epa.gov/lead</a> .
<b>VOC – VOS Statement:</b>	This product contains a maximum of 50 grams of VOC/VOS per liter of coating
<b>Cautions:</b>	<b>CAUTION!</b> <b>Do not take internally. Close container after each use.</b>  <b>KEEP OUT OF REACH OF CHILDREN.</b>

12/23

